

Main

Billets

Plain Round Steel Bars

Deformed Steel Bars

Worldwide Standards  
(Comparisons)

Test Results

## Deformed Steel Bars



No.	Designation	Nominal diameter	Nominal section Area	Inner Diameter	Height of knot		Interval between knots		Unit mass kg/m
		mm	cm <sup>2</sup>		mm	mm	mm	mm	
1.	S.06	6	0.28	5.5	0.3	0.6	4.2	4.7	0.22
2.	S.08	8	0.50	7.3	0.4	0.8	5.6	6.3	0.40
3.	S.10	10	0.79	8.9	0.5	1.0	7.0	7.9	0.62
4.	S.13	13	1.33	12.0	0.7	1.3	9.1	10.2	1.04
5.	S.16	16	2.01	15.0	0.8	1.6	11.2	12.6	1.58
6.	S.19	19	2.84	17.8	1.0	1.9	13.3	14.9	2.23
7.	S.22	22	3.80	20.7	1.1	2.2	15.4	17.3	2.98
8.	S.25	25	4.91	23.6	1.3	2.5	17.5	19.7	3.85
9.	S.29	29	6.63	27.2	1.5	2.9	20.3	22.8	5.18
10.	S.32	32	8.04	30.2	1.6	3.2	22.4	25.1	6.31
11.	S.36	36	10.18	34.0	1.8	3.6	25.2	28.3	7.99
12.	S.40	40	12.57	38.0	2.0	4.0	28.0	31.4	9.88
13.	S.50	50	19.64	48.0	2.5	5.0	38.0	39.3	15.40